



# RUBBER SHEETS

## PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE	TRADE NAME
2001	Oil resistant sheet

POLYMER: NBR	APPLICATION Oil resistant
-----------------	------------------------------

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ASTM D 2240	70	± 5
TENSILE STRENGTH (CR)	MPa	ASTM D 412C	8	min.
ELONGATION AT BREAK (AR)	%	ASTM D 412C	350	min.
TEAR STRENGTH	N/mm (.)	ASTM D 624B	30	min.
ABRASION RESISTANCE	mm <sup>3</sup>	DIN 53516		
SPECIFIC GRAVITY	g/cm <sup>3</sup>	DIN 53479	1,50	± 0,03

AGEING	Δ H	Sh.A3		5
In: Air	Δ CR	%	ASTM D 573	- 20
For: 72 h	Δ AR	%		- 40
At: 100 °C	Δ V	%		

AGEING	Δ H	Sh.A3		10
In: IRM 901	Δ CR	%	ASTM D 471	
For: 72 h	Δ AR	%		
At: 100 °C	Δ V	%		- 10

AGEING	Δ H	Sh.A3		-10
In: IRM 903	Δ CR	%	ASTM D 471	
For: 72 h	Δ AR	%		
At: 100 °C	Δ V	%		10

WORKING TEMPERATURES					
In Air	°C	ASTM D 573	min:	- 20	max: + 100
In Oil	°C	ASTM D 471	min:		max: +100
In Water	°C	ASTM D 471	min:		max: +90

MAIN CHARACTERISTICS					
Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
GOOD/POOR	GOOD	POOR	POOR	GOOD	POOR

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.