



RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE
3012 65

TRADE NAME
chloroprene sheet 65 ShA3

VERS: 001

POLYMER:
CR

DATA: 05/09/2017

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ISO 7619	65	± 5
TENSILE STRENGTH (CR)	MPa	ISO 37 - 1	9	min.
ELONGATION AT BREAK (AR)	%	ISO 37 - 1	250	min.
TEAR STRENGTH	N/mm (.)	ISO 34 C	25	min.
ABRASION RESISTANCE	mm ³	ISO 4649		
SPECIFIC GRAVITY	g/cm ³	ISO 2781	1,48	± 0,03

WORKING TEMPERATURES

In Air	°C	ISO 188	min:	-20	max:	+90
In Oil	°C	ISO 1817	min:		max:	+23
In Water	°C	ISO 1817	min:		max:	+90

MAIN CHARACTERISTICS

Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
GOOD	GOOD	GOOD/SUFFICIENT	SUFFICIENT	SUFFICIENT	SUFFICIENT

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.