



RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE	TRADE NAME
1010	Standard abrasion resistant sheet

POLYMER: NR/BR	APPLICATION Anti-abrasive
-------------------	------------------------------

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ASTM D 2240	60	± 5
TENSILE STRENGTH (CR)	MPa	ASTM D 412C	12	min.
ELONGATION AT BREAK (AR)	%	ASTM D 412C	350	min.
TEAR STRENGTH	N/mm (.)	ASTM D 624B	40	min.
ABRASION RESISTANCE	mm ³	DIN 53516	150	max.
SPECIFIC GRAVITY	g/cm ³	DIN 53479	1,22	± 0,03

AGEING In: Air For: 72 h At: 70 °C	Δ H	Sh.A3	ASTM D 573	9
	Δ CR	%		- 30
	Δ AR	%		- 40
	Δ V	%		
AGEING In: Water For: 72 h At: 50 °C	Δ H	Sh.A3	ASTM D 471	-5
	Δ CR	%		
	Δ AR	%		
	Δ V	%		+ 5

WORKING TEMPERATURES						
In Air	°C	ASTM D 573	min:	- 30	max:	+ 80
In Oil	°C	ASTM D 471	min:		max:	
In Water	°C	ASTM D 471	min:		max:	+80

MAIN CHARACTERISTICS					
Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
GOOD/EXCELLENT	GOOD/EXCELLENT	GOOD/EXCELLENT	POOR	UNSUITABLE	POOR

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.