

## **RUBBER SHEETS**

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

code 1011 80

INDUSTRIAL BLACK SHEET 80 S

VERS:

003

DATA: 03/03/2023

POLYMER: SBR

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ISO 7619	80	± 5
TENSILE STRENGTH (CR)	MPa	ISO 37 - 1	3	min.
ELONGATION AT BREAK (AR)	%	ISO 37 - 1	200	min.
TEAR STRENGTH	N/mm (.)	ISO 34 C	15	min.
ABRASION RESISTANCE	mm3	ISO 4649		
SPECIFIC GRAVITY	g/cm3	ISO 2781	1,65	± 0,03

WORKING TEMPERATURES						
In Air	°C	ISO 188	min:	-20	max:	+70
In Oil	°C	ISO 1817	min:		max:	
In Water	°C	ISO 1817	min:		max:	+70

Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
SUFFICIENT	SUFFICIENT	SUFFICIENT	GOOD/SUFFICIENT	UNSUITABLE	UNSUITABLE

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.