



RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE
4444 60

TRADE NAME
Super EPDM Sheet

VERS: **001**

POLYMER:
EPDM

DATA: **05/09/2017**

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ISO 7619	60	± 5
TENSILE STRENGTH (CR)	MPa	ISO 37 - 1	12	min.
ELONGATION AT BREAK (AR)	%	ISO 37 - 1	450	min.
TEAR STRENGTH	N/mm (.)	ISO 34 C	30	min.
ABRASION RESISTANCE	mm ³	ISO 4649		
SPECIFIC GRAVITY	g/cm ³	ISO 2781	1,10	± 0,03

AGEING	Δ H	Sh.A3		6
In: Air	Δ CR	%	ISO 188	- 10
For: 72 h	Δ AR	%		- 30
At: 100 °C	Δ V	%		

AGEING	Δ H	Sh.A3		
In: Ozone	Δ CR	%	ISO 1817	OK
For: 72 h	Δ AR	%		
At: 30 °C- 100 pphm- all. 50	Δ V	%		

AGEING	Δ H	Sh.A3		-3
In: Water	Δ CR	%	ISO 1817	
For: 72 h	Δ AR	%		
At: 100 °C	Δ V	%		+ 3

WORKING TEMPERATURES							
In Air	°C	ISO 188	min:	- 40	max:	+ 120	
In Oil	°C	ISO 1817	min:		max:		
In Water	°C	ISO 1817	min:		max:	+100	

MAIN CHARACTERISTICS					
Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
GOOD	GOOD	GOOD/SUFFICIENT	SUFFICIENT	UNSUITABLE	EXCELLENT

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.