



RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE
7001 60 ROSSO

TRADE NAME
Coloured silicone sheet

VERS: **002**

POLYMER:
VMQ (SILICONE)

DATA: **22/03/2019**

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ISO 7619	60	± 5
TENSILE STRENGTH (CR)	MPa	ISO 37 - 1	6	min.
ELONGATION AT BREAK (AR)	%	ISO 37 - 1	300	min.
TEAR STRENGTH	N/mm (.)	ISO 34 C	15	min.
ABRASION RESISTANCE	mm ³	ISO 4649		
SPECIFIC GRAVITY	g/cm ³	ISO 2781	1,19	± 0,03
COMPRESSION SET	%	ISO 815 - 1	30	max.

AGEING In: Air For: 72 h At: 180 °C	Δ H	Sh.A3		10	
	Δ CR	%	ISO 188	- 15	
	Δ AR	%		-30	
	Δ V	%			
AGEING In: Ozone For: 72 h At: 30 °C- 100 pphm- all. 50	Δ H	Sh.A3			
	Δ CR	%	ISO 1431-1	OK	
	Δ AR	%			
	Δ V	%			

WORKING TEMPERATURES						
In Air	°C	ISO 188	min:	-65	max:	+200
In Oil	°C	ISO 1817	min:		max:	
In Water	°C	ISO 1817	min:		max:	+70

MAIN CHARACTERISTICS					
Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
GOOD	GOOD	SUFFICIENT	GOOD	UNSUITABLE	EXCELLENT

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.