



**PHYSICAL PROPERTIES AND THECNICAL INFORMATION**

TRADE NAME		COMPOSITION	
<b>T 120 VIN</b>		<b>PVC</b>	
CELLULAR STUCTURE		OPEN CELL SPONGE PVC	
COLOUR			
HARDNESS	SHORE 00		
DENSITY (Kg/m³)	ISO 845-88	120 ± 20	
COMPRESSION DEFLECTION	DIN 53576	110	
COMPRESSION SET 50%/ 72h 20°C	DIN 53577	1,1%	
WATER ABSORPTION	ASTM D 1056-00	1%	
LINEAR SHRINKAGE	4 h 60°C long.		
ELONGATION AT BREAK	DIN 53571	135%	
TENSILE STRENGTH	DIN 53571		
TEMPERATURE RANGE	CONSTANT	- 20°C / + '65° C	
	INTERMITTENT	70	
RESISTANCE	AIR + U.V.	EXCELLENT	
	OZONE	EXCELLENT	
	OIL	POOR	
	ACIDS	POOR	
	FIRE RESISTANCE ( FMVSS 302)	<b>SELFESTINGUISHING B3</b>	
ENVIRONMENTAL PROTECTION		CFC & HCFC FREE	
RECYCLING		CAN BE RECYCLED	