



PHYSICAL PROPERTIES AND THECNICAL INFORMATION

TRADE NAME		COMPOSITION
T75 EPS		EPDM
CELLULAR STRUCTURE		CLOSED CELL SPONGE RUBBER
COLOUR		BLACK
HARDNESS	SHORE 00	25±5
DENSITY (Kg/m³)	ISO 845-88	75 ± 20
COMPRESSION DEFLECTION	ASTM D1056-00 50% (kPa)	40-80
COMPRESSION SET 50%/ 22h 70°C	ASTM D1056-78	28%
WATER ABSORPTION	ASTM D 1056-78	< 26 %
LINEAR SHRINKAGE	22 h 70°C	< 5%
ELONGATION AT BREAK	ISO 1798-97	≥ 150 %
TENSILE STRENGTH	ISO 1798-97	≥ 200 kPa
TEMPERATURE RANGE	CONSTANT	- 40 °C / + 80° C
	INTERMITTENT	MAX + 100°C
RESISTANCE	AIR + U.V.	EXCELLENT
	OZONE	GOOD
	OIL	POOR
	ACIDS	GOOD
	FIRE RESISTANCE (FMVSS 302)	PASS
ENVIRONMENTAL PROTECTION		CFC & HCFC FREE
RECYCLING		CAN BE RECYCLED