



RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE	TRADE NAME
3016	Insulating Chloroprene Sheet

POLYMER: CR	APPLICATION Chloroprene
----------------	----------------------------

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ASTM D 2240	65	± 5
TENSILE STRENGTH (CR)	MPa	ASTM D 412C	10	min.
ELONGATION AT BREAK (AR)	%	ASTM D 412C	500	min.
TEAR STRENGTH	N/mm (.)	ASTM D 624B	15	min.
ABRASION RESISTANCE	mm ³	DIN 53516		
SPECIFIC GRAVITY	g/cm ³	DIN 53479	1,46	± 0,03

AGEING In: Air For: 72 h At: 70 °C	Δ H	Sh.A3		5
	Δ CR	%	ASTM D 573	- 10
	Δ AR	%		- 20
	Δ V	%		
AGEING In: IRM 903 For: 72 h At: 23°C	Δ H	Sh.A3		-4
	Δ CR	%	ASTM D 471	+ 5
	Δ AR	%		+ 6
	Δ V	%		

WORKING TEMPERATURES						
In Air	°C	ASTM D 573	min:	- 20	max:	+ 90
In Oil	°C	ASTM D 471	min:		max:	+50
In Water	°C	ASTM D 471	min:		max:	+90

MAIN CHARACTERISTICS					
Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
POOR	POOR	GOOD	GOOD	POOR	GOOD

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.