



RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE	TRADE NAME
1002	Super abrasion resistant sheet

POLYMER: NR/BR	APPLICATION Anti-abrasive
-------------------	------------------------------

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ASTM D 2240	65	± 5
TENSILE STRENGTH (CR)	MPa	ASTM D 412C	18	min.
ELONGATION AT BREAK (AR)	%	ASTM D 412C	350	min.
TEAR STRENGTH	N/mm (.)	ASTM D 624B	60	min.
ABRASION RESISTANCE	mm ³	DIN 53516	120	max.
SPECIFIC GRAVITY	g/cm ³	DIN 53479	1,12	± 0,03

AGEING In: Air For: 72 h At: 70 °C	Δ H	Sh.A3	ASTM D 573	8
	Δ CR	%		- 30
	Δ AR	%		- 40
	Δ V	%		
AGEING In: Water For: 72 h At: 50 °C	Δ H	Sh.A3	ASTM D 471	-6
	Δ CR	%		
	Δ AR	%		
	Δ V	%		+ 6

WORKING TEMPERATURES In Air In Oil In Water	°C	ASTM D 573	min:	- 35	max:	+ 80
	°C	ASTM D 471	min:		max:	
	°C	ASTM D 471	min:		max:	+80

MAIN CHARACTERISTICS					
Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
EXCELLENT	EXCELLENT	EXCELLENT	POOR	UNSUITABLE	POOR

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.